

TAKATA QUANTUM *X-mile 002*

HYDROLYSIS TYPE TIN-FREE SELF-POLISHING ANTIFOULING COATING N02102

PRODUCT DESCRIPTION New Generation hydrolyzable type tin-free self-activating antifouling paint
& INTENDED USES

FEATURES	<ul style="list-style-type: none"> - Silyl methacrylate antifouling paint - Lower friction resistance by unique technology of rheology smoothness control - Better anti-crack property - Environmentally friendly - Self-polishing efficiency by hydrolysis - Long antifouling property
----------	---

COLOUR(S)	Brick (Finish colour), Maroon
-----------	-------------------------------

APPLICATION METHOD	Airless spray : Recommended Nozzle tip : Graco 617-623 Fluid pressure : 150kg/cm ² Thinning : 0~5% by volume Conventional spray, brush or roller
--------------------	---

THINNER	Thinner No.16 (Japan), Thinner No.7 (Outside of Japan)
---------	--

MIXING RATIO	Ready to use Package : 20kg (Japan), 18L (Outside of Japan)
--------------	--

POT LIFE	【Temperature】	5 °C	10 °C	20 °C	30 °C
		--	--	--	--

TYPICAL FILM THICKNESS	【Wet】	224 μm
	【Dry】	120 μm

SOLID VOLUME RATIO	54 %
--------------------	------

SPREADING RATE	【Theoretical】	4.4 m ² /litre
	【Practical】	Varies depending on surface conditions, environment, application, etc.

DRYING TIME	【Temperature】	5 °C	10 °C	20 °C	30 °C
	【Set to touch】	1 hr.	1 hr.	30 min.	20 min.
	【Dry Hard】	6 hrs.	5 hrs.	4 hrs.	3 hrs.
	【Before Flooding】	17 hrs.	14 hrs.	12 hrs.	10 hrs.

OVERCOATING INTERVAL	【Minimum】	12 hrs.	10 hrs.	9 hrs.	8 hrs.
	【Maximum】	--	--	--	--

The above figures are described at 120 microns DFT.

SHELF LIFE	9 months
------------	----------