## KANSAI PAINT MARINE CO., LTD. KANSAI PAINT



## EPOMARINE AC (M)

SHELF LIFE

12 months

PRODUCT DESCRIPTION & INTENDED USES	Universal anti-corrosive paint for ship bottoms, boottops, topsides, exposed decks and other exposed parts					
FEATURES	<ul> <li>Excellent corrosion resistance</li> <li>Can be overcoated with unlimited coating interval</li> <li>High-build applicability</li> <li>Coloured finish application</li> <li>Good compatibility with a wide range of topcoats</li> <li>Excellent antiabrasion and impact-resistance properties</li> </ul>					
COLOUR(S)	Grey and Brown					
APPLICATION METHOD	Airless spray : Recommended Nozzle tip : $0.023 \sim 0.027''$ Fluid pressure : $100 \sim 150 \text{kg/cm}^2$ Thinning : $0 \sim 8\%$ by volume Conventional spray, brush or roller					
THINNER	Thinner No.17					
MIXING RATIO	Two-pack (Base/Hardener = 70/10 by wt.)					
POT LIFE	[Temperature	e]	5 °C (16) hrs.	10 ℃ 12 hrs.	20 °C 8 hrs.	30 ℃ 6 hrs.
TYPICAL FILM THICKNESS	【Wet】 【Dry】	194 μn 125 μn				
SOLID VOLUME RATIO	64 %					
SPREADING RATE	<ul> <li>[Theoretical] 5.1 m²/litre</li> <li>[Practical] Varies depending on surface conditions, environment, application, etc.</li> </ul>					
DRYING TIME	【Temperature 【Set to touch 【Dry Hard】 【Before Flood	]	5 °C (3) hrs. (24) hrs. (14) days	10 ℃ 3 hrs. 16 hrs. 7 days	20 °C 2 hrs. 10 hrs. 7 days	30 °C 1 hr. 8 hrs. 5 days
OVERCOATING INTERVAL		-		=	16 hrs.  h water hosin e for details.	12 hrs.  g should be required t