KANSAI PAINT MARINE CO., LTD. KANSAI PAINT



PLATINITE R

ALUMINIUM PAINT	N11050
PRODUCT DESCRIPTION & INTENDED USES	Aluminium paint for machinery, pipes, rails and interior surface in funnel that can withstand continuous exposure up to 100°C and up to 150°C for a short while.
FEATURES	Good heat resistanceGood weathering resistance

COLOUR(S)	Silver						
APPLICATION METHOD	Airless spray : Recommended Nozzle tip : $0.019 \sim 0.021''$ Fluid pressure : $100 \sim 150 \text{kg/c} \text{m}^2$ Thinning : $0 \sim 5\%$ by volume Conventional spray, brush or roller						
THINNER	Thinner No. 2						
MIXING RATIO	Ready to use						
POT LIFE	[Temperature]	5 °C	10 ℃	20 ℃ 	30 ℃ 		
TYPICAL FILM THICKNESS	Silver [Wet] 42 μ m [Dry] 20 μ m						
SOLID VOLUME RATIO	48 %						
SPREADING RATE	[Theoretical] 24.0 m²/litre [Practical] Varies depending on surface conditions, environment, application, etc.						
DRYING TIME	【Temperature】 【Set to touch】 【Dry Hard】 【Before Flooding】	5 ℃ 2 hrs. 6 hrs.	10 ℃ 2 hrs. 5 hrs.	20 °C 1 hr. 3 hrs.	30 ℃ 1 hr. 2 hrs.		
OVERCOATING INTERVAL	[Minimum] [Maximum]	24 hrs. 	20 hrs. 	16 hrs. 	12 hrs. 		
SHELF LIFE	12 months						